

High Performance WATERPROOF

CORROSION BLOCK GREASE out performs lithium and most synthetic greases and meets or exceeds requirements for NLGI Service Classifications GC-LB (automotive wheel bearing and chassis lubricants), conforming to ASTM D4950 performance requirements.

PERFORMANCE FEATURES

- Waterproof
- Multi grease compatible
- Excellent extreme pressure (EP) properties
- · Excellent thermal/oxidative stability
- · Resists bleeding or melting at high temperatures
- Suitable for sealed for life applications
- · Use in electrical applications that require grease
- Workplace safe and environmentally friendly
- Out performs competitive grease 5:1





25002 25003

25014 2 oz. Tube 3 oz. Cartridge 14 oz. Cartridge

25016 16 oz. Tub



TECH DATA

Properties	Test Method	Found	Properties	Test Method	Found
4-Ball Wear Test - Scar Diameter	ASTM D-2266	0.40mm	N.L.G.I. Grade	ASTM D-217	#2
4-Ball EP - Load Wear Index	ASTM D-2596	100	Dropping Point	ASTM D-2265	536°F/280°C
4- Ball EP - Weld Point	ASTM D-2596	500kg	Base Oil Viscosity, @104°F / 40°C	ASTM D-445	119 cSt
Rust Protection	ASTM D-1743	PASS	Base Oil Viscosity, @ 212°F / 100°C	ASTM D-445	11.9 cSt
Wheel Bearing Life	ASTM D-3527	320hrs	Penetration @25°C - Unworked	ASTM D-217	278
Water Washout @ 175°F	ASTM D-1264	1.8%	Penetration @25°C - 60 Strokes	ASTM D-217	282
Mobility @ 0°F	USS	12g/min.	Penetration @25°C - 100,000 Strokes	ASTM D-217	330
Low Temperature Torque @ -40° C	ASTM D-4693	6.7 Nm	Timken OK Load	ASTM D-2509	60 lbs

All technical information, recommendation and statements contained herein are based on tests Lear Chemical believes to be reliable. It is offered in good not under our direct control. Liability is limited to the net purchase price of the product. Lear Chemical Research Corp.





LEAR CHEMICAL RESEARCH CORPORATION

1-800-BLOCK-IT (256-2548) or (905) 564-0018 info@learchem.com www.corrosionblock.com

